

## TEST REPORT

(Electronic version)



VERIFICATION WEBSITE: www.gtt.net.cn VERIFICATION CODE: TF0G-1795-04

DATE: 2018-06-16

No:180156940

SHANGHAI SHUOTE NONWOVENS CO., LTD

NO. 8399, TINGFENG ROAD, FENGJING INDUSTRIAL PARK, JINSHAN DISTRICT, SHANGHAI

CHINA

THREE (3) PIECES OF DUPONT™SORONA®INSULATION

COLOR: WHITE

APPLICANT:

INGREDIENTS OF FIBRE: 100%POLYESTER

SIZE: STS-1N WEIGHT: 250g/m<sup>2</sup>

DATE RECEIVED/DATE TEST STARTED: 2018-06-12 15:45

CONCLUSION:

THERMAL RESISTANCE

"M" -MEET CLIENT'S REQUIREMENT "F" -BELOW CLIENT'S REQUIREMENT "---" -NO COMMENT "N" -HALF GRADE LOW "L" -ONE GRADE LOW

REMARK:

IN THIS REPORT, THE SAMPLES ARE TESTED UNDER PRESCRIBED ENVIRONMENTAL CONDITIONS IN THE CORRESPONDING STANDARDS, UNLESS OTHERWISE NOTED. COPIES OF THE REPORT ARE VALID ONLY RE-STAMPED.

THE EXPERIMENT WAS CARRIED OUT AT No. 1-2, ZHUJIANG ROAD, CHAOTIAN INDUSTRIAL ZONE, SHILOU, PANYU DISTRICT, GUANGZHOU.

AUTHORIZED SIGNATORY: Wen Feng SENIOR ENGINEER

page 1 of 2

总部:广州市番禺区珠江路1号 花都实验室:广州市花都区狮岭镇旗岭河滨西路1号 海珠工作站:广州市海珠区滨江中路草芳围35号之二 电话:020-61994598/61994599 电话:020-37721161 电话:020-34402327



## TEST REPORT (Electronic version)

No:180156940

THERMAL RESISTANCE

(GB/T 11048-2008, SWEATING HOT PLATE ) (GB/T 11048-2008 MOD ISO 11092:1993) THERMAL RESISTANCE 0.771K • m<sup>2</sup> /W CLO 4.98clo

——End of Report—— page 2 of 2

总部:广州市番禺区珠江路1号

花都实验室: 广州市花都区狮岭镇旗岭河滨西路1号 海珠工作站:广州市海珠区滨江中路草芳围35号之二

电话:020-61994598/61994599 电话:020-37721161 电话:020-34402327