

# TEST REPORT

(Electronic version)



No:190370513

VERIFICATION WEBSITE: [www.gttc.net.cn](http://www.gttc.net.cn)

VERIFICATION CODE: NQFB-1218-14



ISSUE DATE:2019-12-04

APPLICANT: SHANGHAI SHUOTE NONWOVENS CO.,LTD  
ADDRESS: NO.8399, TINGFENG ROAD, FENGJING INDUSTRIAL PARK, JINSHAN DISTRICT, SHANGHAI  
CHINA

APPLICANT PROVIDED SAMPLE DESCRIPTION:

ONE(1) PIECE OF FILLING MATERIAL(DUPONT SORONA INSULATION(DPD-3) 200g/m<sup>2</sup> )

COLOR: WHITE

INGREDIENTS OF FIBRE: 100%POLYESTER

SIZE: DPD-3

WEIGHT: 200g/m<sup>2</sup>

DATE RECEIVED/DATE TEST STARTED: 2019-11-30

CONCLUSION:

THERMAL RESISTANCE

---

NOTE: "M" -MEET THE STANDARD'S REQUIREMENT "F" -FAIL TO MEET THE STANDARD'S REQUIREMENT  
"---" -NO COMMENT

REMARK:


ALL THE TESTED ITEMS ARE TESTED UNDER THE STANDARD CONDITION (EXCEPT FOR INDICATION).

COPIES OF THE REPORT ARE VALID ONLY RE-STAMPED.

THE EXPERIMENT WAS CARRIED OUT AT No.1, ZHUJIANG ROAD, PANYU DISTRICT, GUANGZHOU, GUANGDONG, P. R. CHINA.

APPROVED BY:

Ming Fang ENGINEER



PAGE 1 OF 2

# TEST REPORT

(Electronic version)

No:190370513

---

## THERMAL RESISTANCE

(GB/T 11048-2008, SWEATING HOT PLATE)

(GB/T 11048-2008 MOD ISO 11092:1993)

THERMAL RESISTANCE

0.696K · m<sup>2</sup> /W

CLO

4.49clo

---

————End of Report————

PAGE 2 OF 2