

TEST REPORT

(Electronic version)

DATE: 2018-09-25



VERIFICATION WEBSITE: www.gtt.net.cn VERIFICATION CODE: NXJV-6904-44



No:180308649

APPLICANT: SHANGHAI SHUOTE NONWOVENS CO., LTD

NO. 8399, TINGFENG ROAD, FENGJING INDUSTRIAL PARK, JINSHAN DISTRICT, SHANGHAI

CHINA

THREE (3) K-2 BAGS

COLOR: WHITE

INGREDIENTS OF FIBRE: 100%POLYESTER

WEIGHT: 240g/m²

DATE RECEIVED/DATE TEST STARTED: 2018-09-18 12:00

CONCLUSION:

THERMAL RESISTANCE

NOTE: "M"-MEET CLIENT'S REQUIREMENT "F"-BELOW CLIENT'S REQUIREMENT "---"-NO COMMENT "N"-HALF GRADE LOW "L"-ONE GRADE LOW

REMARK

IN THIS REPORT, THE SAMPLES ARE TESTED UNDER PRESCRIBED ENVIRONMENTAL CONDITIONS IN THE CORRESPONDING

STANDARDS, UNLESS OTHERWISE NOTED.
COPIES OF THE REPORT ARE VALID ONLY RE-STAMPED.

THE EXPERIMENT WAS CARRIED OUT AT No. 1-2, ZHUJIANG ROAD, CHAOTIAN INDUSTRIAL ZONE, SHILOU, PANYU DISTRICT, GUANGZHOU.

AUTHORIZED SIGNATORY:
Wen Feng SENIOR ENGINEER

冯文

page 1 of 2

总部:广州市番禺区珠江路1号 花都实验室:广州市花都区狮岭镇旗岭河滨西路1号 海珠工作站:广州市海珠区滨江中路草芳围35号之二 电话:020-61994598/61994599 电话:020-37721161 电话:020-34402327



TEST REPORT (Electronic version)

No:180308649

THERMAL RESISTANCE

(GB/T 11048-2008, SWEATING HOT PLATE) (GB/T 11048-2008 MOD ISO 11092:1993) THERMAL RESISTANCE 0.874K • m² /W CLO 5.64clo

——End of Report—— page 2 of 2

总部:广州市番禺区珠江路1号 花都实验室: 广州市花都区狮岭镇旗岭河滨西路1号 海珠工作站:广州市海珠区滨江中路草芳围35号之二

电话:020-61994598/61994599 电话:020-37721161 电话:020-34402327