

TEST REPORT

(Electronic version)



No:180308650

VERIFICATION WEBSITE: www.gtt.net.cn

VERIFICATION CODE: KBHM-7304-24

DATE:2018-09-22



APPLICANT: SHANGHAI SHUOTE NONWOVENS CO., LTD
NO. 8399, TINGFENG ROAD, FENGJING INDUSTRIAL PARK, JINSHAN DISTRICT, SHANGHAI
CHINA

THREE (3) FTM-R BAGS

COLOR: WHITE

INGREDIENTS OF FIBRE: 100%POLYESTER

WEIGHT: 240g/m²

DATE RECEIVED/DATE TEST STARTED: 2018-09-18 12:00

CONCLUSION:

THERMAL RESISTANCE

NOTE: "M" -MEET CLIENT'S REQUIREMENT "F" -BELOW CLIENT'S REQUIREMENT
"---" -NO COMMENT "N" -HALF GRADE LOW "L" -ONE GRADE LOW

REMARK:


IN THIS REPORT, THE SAMPLES ARE TESTED UNDER PRESCRIBED ENVIRONMENTAL CONDITIONS IN THE CORRESPONDING STANDARDS, UNLESS OTHERWISE NOTED.

COPIES OF THE REPORT ARE VALID ONLY RE-STAMPED.

THE EXPERIMENT WAS CARRIED OUT AT No. 1-2, ZHUJIANG ROAD, CHAOTIAN INDUSTRIAL ZONE, SHILOU, PANYU DISTRICT, GUANGZHOU.

AUTHORIZED SIGNATORY:

Wen Feng SENIOR ENGINEER



TEST REPORT

(Electronic version)

No:180308650

THERMAL RESISTANCE

(GB/T 11048-2008, SWEATING HOT PLATE)

(GB/T 11048-2008 MOD ISO 11092:1993)

THERMAL RESISTANCE 0.858K · m² /W

CLO 5.53clo

————End of Report————

page 2 of 2