

zhoumeifang@chinastwf.cn

Arrived:

Completed:

Normal (8-10 Days)

Mon 1 April 2019

Mon 22 April 2019



MA | 161110261827




Maryra

Shanghai Shuote Nonwovens Co., Ltd No. 8399, Tingfeng Road, Fengjing Industrial Park Jinshan District, Shanghai

China

Sample Type:Synthetic FiberShipped By:SF 237685965333

Sample Identification: FTM-Z



This analysis represents (within normal testing variances) the test results from the sample(s) submitted. The analysis may not represent the entire lot, batch or production run. In no event shall IDFL be responsible or liable for any direct, indirect, punitive, incidental, special, or consequential damages whatsoever arising out of or connected with the use of, misuse of, or reliance upon such results or analysis. This test report is subject to the Terms and Conditions found at www.idfl.com.

IDFL LABORATORY AND INSTITUTE

IDFL SALT LAKE 1455 South 1100 East Salt Lake City, UT 84105 USA +1 801 467 7611

info@idfl.com

IDFL EUROPE AG Zürcherstrasse 282 CH-8500 Frauenfeld Switzerland +41 52 765 1574 europe@idfl.com IDFL CHINA Tonghui Mid-Road 688, Xiaoshan Hangzhou Zhejiang 311200 China +86 571 8273 6561 china@idfl.com IDFL TAIPEI 2F., No. 163 Sec. 2, Wenhua Rd. Banqiao District, New Taipei City Taiwan +886 2 2259 1178

taiwan@idfl.com

Approved By www.idfl.com Client 12237 XS

Page 1 of 2



IDFL # 19-284527

Date: 22-Apr-2019

Thermal Resistance of Batting Systems Using a Hot Plate ASTM D1518 Option 1: Still Air Condition

Test Conditions			Bare Plate Total Insulation	Total Insulation	Intrinsic Insulation	
Avg Amb (C)	Hot Plate Temp (C)	Avg RH	RCT0 (K*m²/W)	RCT (K*m²/W)	RCF (K*m²/W)	Clo
17.33	35.0	37.1%	0.099	0.746	0.647	4.18

Comments:

IDFL TAIPEI