

## TEST REPORT (Electronic version)

### VERIFICATION WEBSITE: www.gtt.net.cn VERIFICATION CODE: RRCH-5431-14

DATE: 2017-12-08

No:170397872

APPLICANT: SHANGHAI SHUOTE NONWOVENS CO., LTD NO. 8399, TINGFENG ROAD, FENGJING INDUSTRIAL PARK, JINSHAN DISTRICT, SHANGHAI CHINA

ONE (1) PIECE OF PADDING (FLETHERMO®)

COLOR: WHITE

**INGREDIENTS OF FIBRE: 100%POLYESTER** 

SIZE: FTM-HT

WEIGHT:  $180 \text{g/m}^2$ 

DATE RECEIVED/DATE TEST STARTED: 2017-12-04 15:45

CONCLUSION:

THERMAL RESISTANCE

"M" -MEET CLIENT'S REQUIREMENT "F" -BELOW CLIENT'S REQUIREMENT "---" -NO COMMENT "N" -HALF GRADE LOW "L" -ONE GRADE LOW NOTE:

REMARK:

IN THIS REPORT, THE SAMPLES ARE TESTED UNDER PRESCRIBED ENVIRONMENTAL CONDITIONS IN THE CORRESPONDING STANDARDS, UNLESS OTHERWISE NOTED. COPIES OF THE REPORT ARE VALID ONLY RE-STAMPED.

THE EXPERIMENT WAS CARRIED OUT AT No. 1-2, ZHUJIANG ROAD, CHAOTIAN INDUSTRIAL ZONE, SHILOU TOWN, PANYU DISTRICT, **GUANGZHOU** 

AUTHORIZED SIGNATORY: Nan Ma ENGINEER



page 1 of 2



# TEST REPORT

(Electronic version)

### No:170397872

#### THERMAL RESISTANCE

(GB/T 11048-2008, SWEATING HOT PLATE ) (GB/T 11048-2008 MOD ISO 11092:1993) THERMAL RESISTANCE 0.489K • m<sup>2</sup> /W CLO 3.15<u>clo</u>

page 2 of 2 ——End of Report—— 电话:020-61994598/61994599 传真:020-66364200 番禺实验室(总部):广州市番禺区石楼潮田工业区珠江路1-2号 传真:020-34402337 海珠实验室:广州市海珠区滨江中路草芳围35号之二 电话:020-34402327 上海工作站:上海市静安区北京西路1701号1607室 电话:021-51572226 中大轻纺城工作站:广州市海珠区瑞康路389号长江轻纺城南区3层SC044号 电话:020-89637467 电话:021-51572226 传真:021-51572225 传真:020-89637467 白马服装城工作站:广州市越秀区站南路16号白马大厦负一层客户服务中心旁 电话:020-86663865 传真:020-86663865