

TEST REPORT

Number : SHAT07561691

Applicant : SHANGHAI SHUOTE NON-WOVEN CO., LTD.
NO.8399 TINGFENG RD, SHANGHAI, CHINA

Date : Mar 08, 2023

Attn : HU LING LIAN

Sample Description As Declared :

No. Of Sample : One
Fibre Content : 100% Polyester
Material : 50cmx50cm Mockup Filled With 38.5 Grams White Down Like
Finishing : -
End Uses : -
Colour : White
Style No. : UF-R3
Order No./PO No. : -
Buyer's Name : -
Manufacturer's Name : SHANGHAI SHUOTE NONWOVENS CO., LTD
Ref. : Goods Exported To: USA
Country Of Origin: China

Applicant's Provided Care Instruction/Label :

-

Date Sample Received : Mar 03, 2023
Date Testing Started : Mar 03, 2023

Prepared And Checked By:
For Intertek Testing Services Ltd., Shanghai



Jane Wu
General Manager of Softlines

Intertek Testing Services Ltd., Shanghai

2/F, Building No.4, Shanghai Comalong Technology Service Park,
889 Yishan Road, Shanghai 200233, China

上海天祥质量技术服务有限公司

中国上海宜山路 889 号上海齐来科技服务园区 4 号楼 2 楼 邮编:200233

Tel: +86 21 5339 5999 Fax: +86 21 5426 2030 E-mail: textile.shanghai@intertek.com Website: Intertek.com
Attention is drawn to the terms and conditions printed overleaf

TEST REPORT

Number : SHAT07561691

Tests Conducted (As Requested By The Applicant)

- 1 Thermal Resistance Of Batting Systems Using A Hot Plate (ASTM D1518-14, Option 1):

0.588 k • M²/W

End of Report

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

This report shall not be reproduced except in full, without written approval of the laboratory.